

Value

# ES02 EPDM





## EPDM 60 SHEETING FOR TECHNICAL APPLICATIONS

## **FEATURES**

60 Shore A EPDM.

#### APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general industrial purpose applications in contact with water, oxidizing and non oxidizing diluted acids.

### **ADVANTAGES**

- Very good resistance to ozone and ageing
- Excellent temperature resistance (-40/+120°C)
- Excellent resistance to most inorganic or corrosive chemical products
- Highly resistant to mineral acids, detergents, phosphoric ethers, ketones, alcohols, or low molecular weight glycols
- Very good performance with hot water or high pressure steam
- Good mechanical properties
- Matte finish to guarantee a good surface finished quality and to secure an easy unrolling.

## **BENEFITS**

- Service life
- Performance
- Safety

## **MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES**

**Measured characteristics** 

Standard

| MECHANICAL   |  |                   |                       |         |  |  |
|--|--|-------------------|-----------------------|---------|--|--|
|  |  | EPDM              | I                     |         |  |  |
|  |  | 1.22 ±0.05        | g/cm <sup>3</sup>     |         |  |  |
|  | ASTM D2240   | 60 ±5             | Shore A               |         |  |  |
|  | ISO 37   | ≥10               | MPa                   |         |  |  |
|  | ISO 37   | ≥500              | %                     |         |  |  |
|  | ISO 34-1   | ≥30               | N/mm                  |         |  |  |
| Comp   | ISO 815-1  | ≤20               | %                     |         |  |  |
| TEMPERATURE  |  |                   |                       |         |  |  |
| Working temperature  |  |                   | -40/+120              | °C      |  |  |
| AGEING   |  |                   |                       |         |  |  |
| $\Delta$ Hardness after 72h at 100°  |  | ASTM D573         | ≤5                    | Shore A |  |  |
| Δ Tensil   | ASTM D573  | ≤±10              | %                     |         |  |  |
| $\Delta$ Elongation at break after 72h at 100°C  |  | ASTM D573         | ≤-30                  | %       |  |  |
| Ozone resistance, 200pphm, 96h, 30°C, 20%  |  | ASTM D1149 type A | No crack              |         |  |  |
| CHEMICAL RESISTANCE  |  |                   |                       |         |  |  |
| Diluted acids and bases  | Concentrated acids and bases   | Ozone             | Oils and hydrocarbons |         |  |  |
| Very good  | Good   | Very good         | Non suitable          |         |  |  |
| IDENTIFICATION   |  |                   |                       |         |  |  |
| Branding   | Without.   |                   |                       |         |  |  |
| Packaging  | Thickness ≤6mm rolled on cardboard tube Ø 80mm.<br>Thickness >6mm in roll.   |                   |                       |         |  |  |
| Wrapping   | Black polyethylene film.   |                   |                       |         |  |  |
| Labelling  | Self-adhesive label indicating product name, dimensions, area in m2, nominal weight, and product code to allow product traceability. |                   |                       |         |  |  |
| Unless typographical error, information and figures of our technical datasheet are based on our experience |  |                   |                       |         |  |  |

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

| EPDM      | EPDM 60 SHEETING | ES02     |                 |                           |
|-----------|------------------|----------|-----------------|---------------------------|
| THICKNESS | WIDTH            | LENGTH m | WEIGHT<br>kg/m² | SIDES FINISH              |
| 1±0.2     | 1400 ± 2 %       | 20 ± 2 % | 1.29            | 1 SIDE SMOOTH/1 SIDE MATT |
| 1.5 ±0.25 | 1400 ± 2 %       | 15 ± 2 % | 1.94            | 1 SIDE SMOOTH/1 SIDE MATT |
| 2±0.3     | 1400 ± 2 %       | 15 ± 2 % | 2.58            | 1 SIDE SMOOTH/1 SIDE MATT |
| 3±0.3     | 1400 ± 2 %       | 10 ± 2 % | 3.67            | 1 SIDE SMOOTH/1 SIDE MATT |
| 4±0.4     | 1400 ± 2 %       | 10 ± 2 % | 5.16            | 1 SIDE SMOOTH/1 SIDE MATT |
| 5±0.4     | 1400 ± 2 %       | 10 ± 2 % | 6.45            | 1 SIDE SMOOTH/1 SIDE MATT |
| 6±0.5     | 1400 ± 2 %       | 10 ± 2 % | 7.74            | 1 SIDE SMOOTH/1 SIDE MATT |
| 8±0.7     | 1400 ± 2 %       | 5 ± 2 %  | 10.4            | 1 SIDE SMOOTH/1 SIDE MATT |
| 10±1.0    | 1400 ± 2 %       | 5 ± 2 %  | 12.9            | 1 SIDE SMOOTH/1 SIDE MATT |

