C400
CR SBR

CHLOROPRENE 40 SHEETING FOR TECHNICAL APPLICATIONS

FEATURES
40 Shore A chloroprene.

APPLICATIONS
Gaskets or washers cutting and manufacturing of pieces for general industrial purpose applications in contact with mineral and vegetable oil, non aromatic grease and hydrocarbons.

Non suitable for oxygenated and halogen solvents, aromatic hydrocarbon, mineral and organic acids, washed water.

ADVANTAGES
- Flexible
- Good low temperature resistance
- Good dry high temperature resistance
- Matte finish to guarantee a good surface finished quality and to secure an easy unrolling.

BENEFITS
- Safety
- Economy

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

Measured characteristics	Standard	Value	
MECHANICAL			
Rubber compound - black		CR SBR	
Density		1.33 ±0.05	g/cm³
Hardness	ASTM D2240	40 ±5	Shore A
Tensile strength	ISO 37	≥4	MPa
Elongation at break	ISO 37	≥450	%
Tear resistance	ISO 34-1	≥11	N/mm
Compression set after 22h at 70°C	ISO 815-1	≤40	%
TEMPERATURE			
Working temperature		-30/+90	°C
AGEING			
Δ Hardness after 70h at 70°C	ASTM D573	≤5	Shore A
Δ Tensile strength after 70h at 70°C	ASTM D573	≤-15	%
Δ Elongation at break after 70h at 70°C	ASTM D573	≤-40	%
OIL RESISTANCE			
Oil IRM 901, Δ volume after 70h at 70°C	ISO 1817	≤26	%
CHEMICAL RESISTANCE			

Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons
Medium	Non suitable	Medium	Medium

IDENTIFICATION	
Branding	Without.
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.
Wrapping	Black polyethylene film.
Labelling	Self-adhesive label indicating product name, dimensions, area in m2, nominal weight, and product code to allow product traceability.

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

CR SBR	CHLOROPRENE 40 SHEETING	C400

THICKNESS mm	WIDTH mm	LENGTH m	WEIGHT kg/m²	SIDES FINISH
2 ±0.3	1400 ± 2 %	15 ± 2 %	2.8	2 SIDES MATT
3 ±0.3	1400 ± 2 %	10 ± 2 %	4.2	2 SIDES MATT
4 ±0.4	1400 ± 2 %	10 ± 2 %	5.6	2 SIDES MATT
5 ±0.4	1400 ± 2 %	10 ± 2 %	6.58	1 SIDE SMOOTH/1 SIDE MATT
6 ±0.5	1400 ± 2 %	10 ± 2 %	7.9	1 SIDE SMOOTH/1 SIDE MATT

TRELLEBORG